

RTP 4183

Polyetherketoneketone

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.

General Information			
Filler / Reinforcement	Carbon Fiber,20% Filler by Weight		
Features	High Heat Resistance		
	High Strength		
RoHS Compliance	Contact Manufacturer		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.37	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.10 to 0.20	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.12	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	125		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	25500	MPa	ASTM D638
Tensile Strength (Yield)	276	MPa	ASTM D638
Tensile Elongation (Break)	1.9	%	ASTM D638
Flexural Modulus	17200	MPa	ASTM D790
Flexural Strength (Yield)	379	MPa	ASTM D790
Compressive Strength	262	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	80	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	800	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	288	°C	ASTM D648
Glass Transition Temperature	156	°C	ASTM E1356
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+5	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94

Injection	Nominal Value	Unit
Rear Temperature	357 to 399	°C
Middle Temperature	357 to 399	°C
Front Temperature	357 to 399	°C
Mold Temperature	204 to 232	°C
Injection Pressure	68.9 to 138	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

