

# MTM® 28S-6

Epoxy; Epoxide

Cytec Industries Inc.

## Message:

MTM® 28S-6 is a 120°C (248°F) curing epoxy resin formulated for tube rolling applications.

General Information	
Filler / Reinforcement	Aramid Fiber
	Carbon Fiber
	Glass Fiber
Features	Autoclavable
	Heat Cure
Uses	Rods
	Tubing
Appearance	Colors Available
Forms	Fabric
Processing Method	Press Molding
	Vacuum Forming

Physical	Nominal Value	Unit
Specific Gravity <sup>1</sup>	1.23	g/cm <sup>3</sup>
Thermal	Nominal Value	Unit
Glass Transition Temperature <sup>2</sup>	115	°C

NOTE	
1.	Cured resin
2.	DMA E' onset Tg, 1 hour at 120°C (248°F)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT