

Jam PE 30505

Linear Low Density Polyethylene
Jam Petrochemical Company

Message:

Jam PE 30505 is a Linear Low Density Polyethylene product. It can be processed by rotational molding and is available in Africa & Middle East.

General Information			
Processing Method	Rotational Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.930	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	5.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, Compression Molded	16.3	MPa	
Break, Compression Molded	14.0	MPa	
Tensile Elongation (Break, Compression Molded)	> 800	%	ASTM D638
Flexural Modulus (Compression Molded)	550	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	No Break		ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	104	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT