

Axial PVC 22905

Flexible Polyvinyl Chloride

Axial Corporation

Message:

Non-lead tray cable jacket for 75C maximum service temperature.

General Information			
Uses	Cable Jacketing		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.33 to 1.37	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	87 to 93		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
--	22.1	MPa	
100% Strain	13.1	MPa	
Tensile Elongation (Break)	320	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature ¹	-30.0	°C	ASTM D746
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	32	%	ASTM D2863
Extrusion	Nominal Value	Unit	
Melt Temperature	191	°C	
NOTE			
1.	C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT