

Clariant Nylon 6 60G43-L

Polyamide 6
Clariant Corporation

Message:

Clariant Nylon 6 60G43-L is a Polyamide 6 (Nylon 6) material filled with 43% glass fiber. It is available in North America for injection molding. Primary attribute of Clariant Nylon 6 60G43-L: Lubricated.

General Information			
Filler / Reinforcement	Glass Fiber,43% Filler by Weight		
Additive	Lubricant		
Features	Lubricated		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.48	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.30	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	159	MPa	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	10300	MPa	ASTM D790
Flexural Strength	248	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	120	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	216	°C	
1.8 MPa, Unannealed	210	°C	
Melting Temperature	218	°C	
Injection	Nominal Value	Unit	
Drying Temperature	71.1 to 82.2	°C	
Suggested Max Regrind	25	%	
Rear Temperature	210 to 232	°C	
Middle Temperature	227 to 249	°C	
Front Temperature	243 to 266	°C	
Nozzle Temperature	232 to 260	°C	
Mold Temperature	71.1 to 104	°C	
Injection Pressure	34.5 to 138	MPa	
Back Pressure	0.00 to 1.03	MPa	
Screw Speed	30 to 60	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

