

Yuyao PP TL402

Polypropylene

Yuyao Tenglong Plastics Co., Ltd.

Message:

Yuyao PP TL402 is a Polypropylene product filled with 20% mineral. It can be processed by injection molding and is available in Asia Pacific. Applications of Yuyao PP TL402 include appliances, automotive, electrical/electronic applications, furniture and housings.

Characteristics include:

- Flame Rated
- Chemical Resistant
- Good Dimensional Stability
- Good Processability
- Heat Resistant

General Information			
Filler / Reinforcement	Mineral,20% Filler by Weight		
Features	Electrically Insulating		
	Good Chemical Resistance		
	Good Dimensional Stability		
	Good Processability		
	Good Strength		
	High Gloss		
	High Heat Resistance		
Uses	Appliance Components		
	Automotive Applications		
	Electrical/Electronic Applications		
	Furniture		
	Housings		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.50 to 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	40.0	MPa	ASTM D638
Tensile Elongation (Break)	7.0	%	ASTM D638
Flexural Modulus	2300	MPa	ASTM D790
Flexural Strength	50.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area)	5.00	kJ/m ²	ASTM D256
Aging	Nominal Value		
Aging Resistance (150°C)	750		

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	130	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.60 mm	HB		
3.20 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 95.0	°C	
Drying Time	2.0 to 3.0	hr	
Processing (Melt) Temp	195 to 225	°C	
Mold Temperature	45.0 to 80.0	°C	
Injection Pressure	60.0 to 90.0	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

