Electrafil® TPX-PC-02071

Polycarbonate

Techmer Engineered Solutions

Message:

Electrafil® TPX-PC-02071 is a Polycarbonate (PC) product filled with stainless steel fiber. It can be processed by injection molding and is available in North America. Characteristics include: Flame Rated Electromagnetic Shielding (EMI) Flame Retardant

General Information			
Filler / Reinforcement	Stainless Steel Fiber		
Features	Electromagnetic Shielding (EMI)		
	Flame Retardant		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.35	g/cm³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.50	%	ASTM D955
Water Absorption (24 hr)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	75.8	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	3790	MPa	ASTM D790
Flexural Strength	134	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	80	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	1400	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	141	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+4	ohms	ASTM D257
Volume Resistivity	1.0E+4	ohms·cm	ASTM D257
Shielding Effectiveness	50	dB	ASTM D4935
Static Decay	< 0.1	sec	FTMS 101B
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

