Yuyao PP TL303

Polypropylene

Yuyao Tenglong Plastics Co., Ltd.

Message:

Yuyao PP TL303 is a Polypropylene product filled with 30% talc. It can be processed by injection molding and is available in Asia Pacific. Applications of Yuyao PP TL303 include appliances, automotive, electrical/electronic applications, furniture and housings.

Characteristics include:

General Information

Flame Rated Chemical Resistant Good Dimensional Stability Good Processability Heat Resistant

Filler / Reinforcement	Talc,30% Filler by Weight				
Features	Electrically Insulating				
	Good Chemical Resistance				
	Good Dimensional Stability				
	Good Processability				
	Good Strength				
	High Gloss				
	High Heat Resistance				
	A . I'				
Uses	Appliance Components				
	Automotive Applications				
	Electrical/Electronic Applications				
	Furniture				
	Housings				
Processing Method	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.20	g/cm³	ASTM D792		
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.0	g/10 min	ASTM D1238		
Molding Shrinkage - Flow	0.50 to 0.80	%	ASTM D955		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength	50.0	MPa	ASTM D638		
Tensile Elongation (Break)	5.0	%	ASTM D638		
Flexural Modulus	2400	MPa	ASTM D790		
Flexural Strength	60.0	MPa	ASTM D790		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact (Area)	4.00	kJ/m²	ASTM D256		
Thermal	Nominal Value	Unit	Test Method		

Deflection Temperature Under Load	J (1.8		
MPa, Unannealed)	130	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.60 mm	НВ		
3.20 mm	НВ		
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 95.0	°C	
Drying Time	2.0 to 3.0	hr	
Processing (Melt) Temp	195 to 225	°C	
Mold Temperature	45.0 to 80.0	°C	
Injection Pressure	60.0 to 90.0	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

