

RTP 102 CC HI

Polypropylene
RTP Company

Message:
Glass Fiber - High Impact - Chemically Coupled

General Information			
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Features	Chemically Coupled		
	High Impact Resistance		
RoHS Compliance	Contact Manufacturer		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.00	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.30 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3100	MPa	ASTM D638
Tensile Strength	37.9	MPa	ASTM D638
Tensile Elongation (Yield)	7.0 to 9.0	%	ASTM D638
Flexural Modulus	2410	MPa	ASTM D790
Flexural Strength	55.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	160	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	590	J/m	ASTM D4812
Flammability	Nominal Value	Test Method	
Flame Rating (1.50 mm, ** Values per RTP Company testing.)	HB	UL 94	
Additional Information	Nominal Value	Unit	
Primary Additive	15	%	
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	191 to 232	°C	
Mold Temperature	32.2 to 65.6	°C	
Injection Pressure	68.9 to 103	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

