

APEX® 88-N398-J

Flexible Polyvinyl Chloride

Teknor Apex Company

Message:

APEX® 88-N398-J is a Flexible Polyvinyl Chloride material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Important attributes of APEX® 88-N398-J are:
RoHS Compliant
Low Gloss
Typical applications include:
Wire & Cable
Electrical/Electronic Applications

General Information			
Features	Low Gloss		
Uses	Communication Wire Jacketing		
Wire Types	CAT-3		
Agency Ratings	NEC Article 725		
	NEC Article 760		
	NEC Article 800		
	NEC Article 820		
	UL 13		
	UL 1424		
	UL 444		
RoHS Compliance	RoHS Compliant		
Appearance	Opaque		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.39	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	90		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	20.0	MPa	ASTM D638
Tensile Elongation (Break)	300	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	75.0	°C	ASTM D794
Brittleness Temperature	-31.0	°C	ASTM D746
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	32	%	ASTM D2863

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT