

UBE Nylon 1015GU6

Polyamide 6
UBE Industries, Ltd.

Message:
Reinforced with glass fiber, heat stabilized

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
Forms	Pellets		
Part Marking Code	>PA6-GF30<		
Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow	0.70	%	
Flow	0.20	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	1.8	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9800	MPa	ISO 527-2
Tensile Stress (Break)	185	MPa	ISO 527-2
Tensile Strain (Break)	3.5	%	ISO 527-2
Flexural Modulus	9400	MPa	ISO 178
Flexural Stress	285	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength	15	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	220	°C	ISO 75-2/B
1.8 MPa, Unannealed	205	°C	ISO 75-2/A
CLTE - Flow	2.5E-5	cm/cm/°C	ISO 11359-2
Flammability	Nominal Value		Test Method
Flame Rating (0.700 mm)	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

