

# Bayfill® 369 (38:100)

Polyurethane (MDI)

Covestro - PUR

## Message:

Bayfill 369 is a semi-rigid polyurethane foam system designed for automotive interior applications. The Bayfill 369 system is an excellent choice for the production of soft-touch panels, such as instrument panels, door trim, and center consoles. The foam is typically molded in a back-filling process between a soft, exterior skin and a rigid, thermoplastic substrate.

The Bayfill 369 system is supplied as two components. Component A is a polymeric diphenylmethane diisocyanate (PMDI). Component B is a polyol mixture. As with any product, use of the Bayfill 369 system in a given application must be tested (including but not limited to field testing) in advance by the user to determine suitability.

General Information			
Uses	Foam		
	Application in Automobile Field		
	Car interior parts		
	Car interior equipment		
	Car dashboard		
Physical	Nominal Value	Unit	Test Method
Molded Density	147	kg/m <sup>3</sup>	ASTM D3574A
Compression Force Deflection			ASTM D3574C
-- <sup>1</sup>	0.0689	MPa	ASTM D3574C
-- <sup>2</sup>	0.0207	MPa	ASTM D3574C
Compression Set			ASTM D3574D
Cd <sup>3</sup>	66	%	ASTM D3574D
Cd <sup>4</sup>	33	%	ASTM D3574D
Ct <sup>5</sup>	16	%	ASTM D3574D
Ct <sup>6</sup>	33	%	ASTM D3574D
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
-- <sup>7</sup>	0.0965	MPa	ASTM D3574K
--	0.241	MPa	ASTM D3574E
Tensile Elongation			
Fracture <sup>8</sup>	46	%	ASTM D3574K
Fracture	61	%	ASTM D3574E
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	0.123	kN/m	ASTM D3574F
Thermoset	Nominal Value		
Thermoset Components			
Component a	Mixing ratio by weight: 42		
Component B	Mixing ratio by weight: 100		
Additional Information			

#### Part A

Type: Isocyanate

Appearance: Dark brown liquid

Specific Gravity @ 25°C: 1.24

Viscosity @25°C: 60 cps

Flash Point PMCC: 149°C

NCO: 32.2 wt%

#### Part B

Type: Polyol

Appearance: Colorless to light tan viscous liquid

Specific Gravity @ 25°C: 1.03

Viscosity @25°C: 1100 cps

Flash Point PMCC: 117°C

Water: 2 wt%

Hydroxyl Number: 70 KOH/g

Mold Temperature: 38 to 43°C Demold Time: >90 sec Hand Mix Reactivity at 25°C

Cream Time: 9 to 17 sec

Top of Cup Time: 36 to 50 sec

Gel Time: 39 to 53 to sec

Rise Time: 67 to 83 sec

Free-Rise Density: 4.90 to 5.70 lb/ft<sup>3</sup>

Machine Reactivity at 27 to 32°C

Cream Time: 6 to 10 sec

Top of Cup Time: 20 to 22 sec

Gel Time: 27 to 31 sec

Rise Time: 44 to 48 sec

Free-Rise Density: 4.00 to 5.00 lb/ft<sup>3</sup>

Molded Density: 7 to 10.5 lb/ft<sup>3</sup>

#### NOTE

1.	0.5
2.	After J2 Autoclave
3.	After J2 Autoclave, Cd=compression set as a percentage of the original deflection
4.	50, Cd=compression set as a percentage of the original deflection
5.	50%, Ct=compression set as a percentage of the original thickness
6.	After J2 Autoclave, Ct=compression set as a percentage of the original thickness
7.	Dry Heat Aged at 140°C
8.	Dry Heat Aged at 140°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

**Susheng Import & Export Trading Co.,Ltd.**

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

