

Generic Acetal (POM) Copolymer - Metal

Acetal (POM) Copolymer

Generic

Message:

This data represents typical values that have been calculated from all products classified as: Generic Acetal (POM) Copolymer - Metal
This information is provided for comparative purposes only.

General Information		
Filler / Reinforcement	Metal	
Injection	Nominal Value	Unit
Drying Temperature	71.1 - 71.3	°C
Drying Time	1.0 - 1.1	hr
Processing (Melt) Temp	204	°C
Mold Temperature	101 - 102	°C
Injection instructions		

This data represents typical values that have been calculated from all products classified as: Generic Acetal (POM) Copolymer - MetalThis information is provided for comparative purposes only.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

