3M[™] Dyneon[™] PTFE Compound FC 18050

Polytetrafluoroethylene

3M Advanced Materials Division

Message:

3M™ Dyneon™ PTFE Compound FC 18050 is a non-free-flowing suspension PTFE compound containing a 62.5% bronze/graphite filler combination for compression moulding. Special Features Increased thermal dimensional stability Increased surface hardness Improved deformation under load Reduced friction and wear Low moulding pressure High limiting oxygen index (LOI) Low friction behaviour Improved mechanical properties Exceptional temperature resistance Good chemical stability

| General Information | | |
|------------------------|---------------------------------------|--|
| Filler / Reinforcement | Bronze\Graphite, 63% filler by weight | |
| Features | Low friction coefficient | |
| Uses | Seals | |
| | Application in Automobile Field | |

| Forms | Powder | | | |
|------------------------------|---------------------|-------|---------------|--|
| Processing Method | Compression molding | | | |
| Physical | Nominal Value | Unit | Test Method | |
| Specific Gravity | 3.30 | g/cm³ | ASTM D4745-06 | |
| Apparent Density | 0.76 | g/cm³ | ASTM D4894-07 | |
| Molding Shrinkage - Flow | 0.90 | % | ASTM D4894-07 | |
| Hardness | Nominal Value | Unit | Test Method | |
| Durometer Hardness (Shore D) | 71 | | DIN 53505 | |
| Mechanical | Nominal Value | Unit | Test Method | |
| Tensile Strength | 14.4 | MPa | ASTM D4745-06 | |
| Tensile Elongation (Break) | 14 | % | ASTM D4745-06 | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com No. 215, Lianhe North Road, Fengxian District, Shanghai, China

