

Centrex® 813

Acrylonitrile Styrene Acrylate + AES
Network Polymers, Inc.

Message:

Centrex® 813 is an Acrylonitrile Styrene Acrylate + AES (ASA+AES) product. It can be processed by injection molding and is available in North America. Applications of Centrex® 813 include electrical/electronic applications, household applications, marine applications, outdoor applications and sporting goods.

Characteristics include:

- Flame Rated
- REACH Compliant
- RoHS Compliant
- WEEE Compliant
- Impact Resistant

General Information			
UL YellowCard	E51193-101898754		
Features	Good Processability		
	Good Weather Resistance		
	High Gloss		
	High Impact Resistance		
	Low Temperature Impact Resistance		
Uses	Electronic Displays		
	Lawn and Garden Equipment		
	Marine Applications		
	Outdoor Applications		
	Water Sports Equipment		
Agency Ratings	EC 1907/2006 (REACH)		
	EU 2002/96/EC (WEEE)		
RoHS Compliance	RoHS Compliant		
UL File Number	E150937		
Forms	Pellets		
Processing Method	Injection Molding		
Multi-Point Data	Isothermal Stress vs. Strain (ISO 11403-1)		
	Secant Modulus vs. Strain (ISO 11403-1)		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	8.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.60	%	ASTM D955

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	85		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	2000	MPa	ASTM D638
Tensile Strength ² (Yield)	33.8	MPa	ASTM D638
Flexural Modulus - Tangent ³	1930	MPa	ASTM D790
Flexural Strength ⁴	54.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-40°C, 3.18 mm	53	J/m	
23°C, 3.18 mm	410	J/m	
Instrumented Dart Impact			ASTM D3763
-40°C, Total Energy	22.0	J	
23°C, Total Energy	33.0	J	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed, 3.18 mm	70.0	°C	
1.8 MPa, Unannealed, 12.7 mm	77.0	°C	
Vicat Softening Temperature	101	°C	ASTM D1525 ⁵
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	82.2 to 87.8	°C	
Drying Time	2.0	hr	
Suggested Max Moisture	0.10	%	
Suggested Shot Size	50 to 70	%	
Suggested Max Regrind	20	%	
Rear Temperature	238 to 271	°C	
Middle Temperature	238 to 271	°C	
Front Temperature	238 to 271	°C	
Nozzle Temperature	238 to 271	°C	
Processing (Melt) Temp	238 to 271	°C	
Mold Temperature	65.6 to 87.8	°C	
Injection Rate	Moderate-Fast		
Screw L/D Ratio	20.0:1.0		
Screw Compression Ratio	2.5:1.0		
NOTE			
1.	5.1 mm/min		
2.	5.1 mm/min		
3.	1.3 mm/min		
4.	1.3 mm/min		
5.	Rate B (120°C/h), Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

