

Trithene® TS 7035

Low Density Polyethylene

Petroquímica Triunfo

Message:

Trithene®TS 7035 is a low density polyethylene material. This product is available in Latin America and is processed by film extrusion.

Trithene®The main features of TS 7035 are:

Good processability

accessible food

Heat resistance

Typical application areas include:

packing

Movie

food contact applications

General Information			
Features	Low friction coefficient		
	Workability, good		
	Thermal stability, good		
	Compliance of Food Exposure		
Uses	Packaging		
	Films		
	Food packaging		
Agency Ratings	ANVISA n°105/99		
	ASTM D 1248, I, Class A, Cat. 3		
	FDA 21 CFR 177.1520(c) 2.1		
Forms	Particle		
Processing Method	Film extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.924	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.5	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, molding	10.0	MPa	ASTM D638
Fracture, molding	12.0	MPa	ASTM D638
Tensile Elongation (Break, Compression Molded)	540	%	ASTM D638
Coefficient of Friction (vs. Itself - Dynamic, Blown Film)	0.090		ASTM D1894
Films	Nominal Value	Unit	Test Method
secant modulus			ASTM D882

5% secant, MD: 50 µm, blown film	97.0	MPa	ASTM D882
5% secant, TD: 50 µm, blown film	103	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Broken, 50 µm, blown film	20.0	MPa	ASTM D882
TD: Broken, 50 µm, blown film	18.0	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Broken, 50 µm, blown film	410	%	ASTM D882
TD: Broken, 50 µm, blown film	690	%	ASTM D882
Dart Drop Impact (50 µm, Blown Film)	130	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD: 50 µm, blown film	460	g	ASTM D1922
TD: 50 µm, blown film	310	g	ASTM D1922
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	93.0	°C	ASTM D1525
Optical	Nominal Value	Unit	Test Method
Gloss (60°, 50.0 µm, Blown Film)	100		ASTM D2457
Haze (50.0 µm, Blown Film)	8.2	%	ASTM D1003

Additional Information

Film properties taken from 50 µm blown film produced on a 50 mm extruder, L/D=25, die gap=1.0 mm, BUR=2.3:1 Melt Mass-Flow Rate, ASTM D1238, 190°C/2.16 kg: 3.0 to 4.0 g/10 min Density, ASTM D1505: 0.922 to 0.925 g/cm³

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	135 - 150	°C
Cylinder Zone 2 Temp.	145 - 160	°C
Cylinder Zone 3 Temp.	150 - 165	°C
Adapter Temperature	160 - 175	°C

Extrusion instructions

Recommended Blow Up Ratio: 2-3.5:1

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT