

ELASTOSIL® RT 702

Silicone

Wacker Chemie AG

Message:

Silicone Rubber, RTV-2

Household Appliances, Household Appliances

Oven Doors, Household Appliances

General Information			
Features	Heat Cure		
Uses	Adhesives		
	Bonding		
	Sealants		
Processing Method	Heat Reactive Adhesive		
Uncured Properties	Nominal Value	Unit	Test Method
Color	Black		
Density			
--	1.21	g/cm ³	ISO 2781
--	1.21	g/cm ³	DIN 53217
Viscosity	800	Pa·s	DIN EN ISO 3219
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	40		ISO 868
Tensile Strength	6.10	MPa	ISO 37
Tensile Elongation at Break	500	%	ISO 37

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

