NaturePlast PBI 003 BB

Thermoplastic Polyester

NaturePlast

Message:

Biopolyesters commercialized by Natureplast are thermoplastic resins 100% biodegradable and compostable in agreement with standards in use. Biopolyesters can also be partially biobased.

These biopolyesters can be processed on standard equipments.

Markets: bagging, film, food processing industry packaging, cosmetics, horticulture, medical, technical parts...

Properties

Translucency, processing easiness.

Performances close to polyolefins (PE and PP) in terms of thermal and mechanical properties.

38% biobased

General Information			
Features	Comstable		
	Updatable resources		
	Biodegradable		
Uses	Films		
	Lawn and Garden Equipment		
	Bags		
	Engineering accessories		
	Cosmetics		
	Food packaging		
	Medical/nursing supplies		
Appearance	Opacity		
Forms	Particle		
Processing Method	Injection blowing molding		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.26	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR)	20	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	730	МРа	ISO 527-2
Tensile Strain (Break)	330	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	83.0	°C	ISO 75-2/B
Additional Information	Nominal Value	Unit	

Biobased Content 38 %

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

