

Adiprene® LF 751D

Polyurethane (Polyether, TDI)

Chemtura

Message:

ADIPRENE LF 751D is a TDI-terminated polyether prepolymer with extremely low free TDI content. Curing with 4,4'-methylene-bis-(o-chloroaniline), MBCA, yields a high performance 75 Shore D polyurethane elastomer suitable for many high-performance applications.

Features of Adiprene LF 751D include:

Low free TDI content

Low viscosity

Moderate pot life

Excellent high temperature dynamic properties

General Information			
Features	Low Viscosity		
Uses	Wheels		
Processing Method	Casting		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	73 to 75		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Compressive Strength			ASTM D695
5% Strain	15.9	MPa	
10% Strain	27.2	MPa	
15% Strain	35.2	MPa	
20% Strain	45.5	MPa	
25% Strain	55.2	MPa	
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% Strain	37.9	MPa	
200% Strain	44.8	MPa	
Tensile Strength	51.7	MPa	ASTM D412
Tensile Elongation (Break)	230	%	ASTM D412
Tear Strength			
-- ¹	166	kN/m	ASTM D624
Split	25	kN/m	ASTM D470
Thermoset	Nominal Value	Unit	
Pot Life	1.8	min	
Demold Time	15	min	
Uncured Properties	Nominal Value	Unit	
Curing Time (100°C)	16	hr	
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

