

# Zhongfa PA6 BZR16

Polyamide 6

Yuyao Zhongfa Engineering Plastics Co. Ltd.

Message:

Zhongfa PA6 BZR16 is a polyamide 6 (nylon 6) material. This product is available in the Asia-Pacific region and is processed by injection molding. The main characteristics of Zhongfa PA6 BZR16 are: impact resistance.

Typical application areas include:

Electrical/electronic applications

electrical appliances

Tools

Furniture

Automotive Industry

General Information			
Features	Impact resistance, high		
	Low temperature impact resistance		
Uses	Electrical/Electronic Applications		
	Electrical appliances		
	Power/other tools		
	Furniture		
	Application in Automobile Field		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.08	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow	1.5	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	57.0	MPa	ASTM D638
Tensile Elongation (Break)	120	%	ASTM D638
Flexural Modulus	1750	MPa	ASTM D790
Flexural Strength	75.0	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	93.0	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Additional Information			
Notched Izod Impact, ASTM D256: 28 kJ/m <sup>2</sup>			
Injection	Nominal Value	Unit	
Drying Temperature	85.0 - 90.0	°C	
Drying Time	6.0 - 8.0	hr	

Processing (Melt) Temp	235 - 255	°C
Mold Temperature	60.0 - 90.0	°C
Injection Pressure	60.0 - 100	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

