

Pier One POM AH500T-NC010

Acetal (POM) Homopolymer

Pier One Polymers, Inc.

Message:

Pier One POM AH500T-NC010 is an Acetal (POM) Homopolymer material. It is available in North America for injection molding.

Important attributes of Pier One POM AH500T-NC010 are:

Good Toughness

Homopolymer

General Information			
Features	Good Toughness		
	Homopolymer		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.39	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/1.05 kg)	5.0 to 7.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	55.2	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	75	%	ASTM D638
Flexural Modulus (23°C)	2310	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	130	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	78.8	°C	ASTM D648
Peak Melting Temperature	157	°C	ASTM D3418
Injection	Nominal Value	Unit	
Drying Temperature	79.0	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	195 to 215	°C	
Mold Temperature	40.0 to 60.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

