

Staramide BST01

Polyamide 6
Eurostar Engineering Plastics

Message:

Staramide BST01 is an Impact Modified Polyamide 6 Injection Molding Resin

General Information			
Additive	Impact Modifier		
Features	Impact Modified		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm ³	ISO 1183
Molding Shrinkage - Flow ¹	1.5 to 2.0	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2650	MPa	ISO 527-2/1
Tensile Stress (Yield)	70.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	3.8	%	
Break	> 100	%	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ²			ISO 180/1A
-20°C	7.0	kJ/m ²	
23°C	11	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ³ (1.8 MPa, Unannealed, 100 mm Span)	75.0	°C	ISO 75-2/Ae
Vicat Softening Temperature	190	°C	ISO 306/B120
CLTE			ISO 11359-2
Flow : 23 to 60°C	9.1E-5	cm/cm/°C	
Transverse : 23 to 60°C	1.2E-4	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index			IEC 60112
--	600	V	
Solution B	600	V	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm, Tested by E2P)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	75.0 to 85.0	°C	
Drying Time	4.0 to 6.0	hr	

Suggested Max Moisture	0.20	%
Rear Temperature	220 to 230	°C
Middle Temperature	230 to 240	°C
Front Temperature	240 to 250	°C
Processing (Melt) Temp	240 to 250	°C
Mold Temperature	60.0 to 90.0	°C

NOTE		
1.	Tensile Bar	
2.	80*10*4	
3.	120*10*4	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT