

neogol® 90 P UG

Thermoplastic Polyolefin Elastomer

API SpA

Message:

neogol® 90 P UG is a polyolefin thermoplastic elastomer (TPO (POE)) product. It can be processed by co-extrusion molding or injection molding and is available in Europe.

Features include:

Copolymer

good weather resistance

General Information			
Features	Block Copolymer		
	Good weather resistance		
Processing Method	Co-extrusion molding		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.870	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/5.0 kg)	65	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	90		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
--	7.10	MPa	ASTM D638
100% strain	4.80	MPa	ASTM D638
300% strain	5.60	MPa	ASTM D638
Tensile Elongation (Break)	680	%	ASTM D638
Abrasion Resistance	120	mm³	DIN 53516
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ¹	53.0	kN/m	ASTM D624
Compression Set			ASTM D395
23°C, 72 hr	50	%	ASTM D395
70°C, 22 hr	77	%	ASTM D395
Injection	Nominal Value	Unit	
Rear Temperature	155 - 175	°C	
Middle Temperature	160 - 180	°C	
Front Temperature	160 - 180	°C	
Nozzle Temperature	165 - 190	°C	
Mold Temperature	25 - 40	°C	
Injection Rate	Moderate-Fast		

NOTE

1. With Notch

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

