## Baydur® 742 IBS (43 pcf)

Polyurethane (MDI)

Covestro - PUR

## Message:

Baydur 742 IBS is a semirigid polyurethane structural foam system used in the reaction injection molding (RIM) process. This system incorporates a specially engineered interactive blowing system (IBS) and is supplied as two reactive liquid components. Component A is a modified polymeric diphenylmethane diisocyanate (PMDI) prepolymer blend, and Component B is a formulated polyol system containing no CFC- or HCFC-blowing additives. Baydur 742 IBS system is used in the consumer products market for applications requiring some protective cushioning characteristics. The system is typically molded at medium-to-high densities. As with any product, use of the Baydur 742 IBS system in a given application must be tested (including field testing, etc.) in advance by the user to determine suitability.

| General Information                           |                                  |       |                 |
|---|----------------------------------|-------|-----------------|
| Additive                                      | Blowing Agent                    |       |                 |
| Uses  | Structural Foam                  |       |                 |
| Processing Method                             | Reaction Injection Molding (RIM) |       |                 |
| Physical                                      | Nominal Value                    | Unit  | Test Method     |
| Specific Gravity                              | 0.688                            | g/cm³ | ASTM D792       |
| Molding Shrinkage - Flow (12.7 mm)            | 0.90 to 1.1                      | %     | ASTM D955       |
| Hardness                                      | Nominal Value                    | Unit  | Test Method     |
| Durometer Hardness (Shore D, 12.7 mm)         | 50                               |       | ASTM D2240      |
| Mechanical                                    | Nominal Value                    | Unit  | Test Method     |
| Tensile Strength (Break, 12.7 mm)             | 10.3                             | MPa   | ASTM D638       |
| Tensile Elongation (Break, 12.7 mm)           | 140                              | %     | ASTM D638       |
| Flexural Modulus (12.7 mm)                    | 184                              | MPa   | ASTM D790       |
| Flexural Strength (12.7 mm)                   | 10.2                             | MPa   | ASTM D790       |
| Compressive Strength (12.7 mm)                | 3.56                             | MPa   | ASTM D695       |
| Impact  | Nominal Value                    | Unit  | Test Method     |
| Charpy Unnotched Impact Strength <sup>1</sup> | No Break                         |       | Internal Method |
| NOTE  |                                  |       |                 |
| 1.  | 0.5 in                           |       |                 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com No. 215, Lianhe North Road, Fengxian District, Shanghai, China

