

# Duron PBT 30GF

Polybutylene Terephthalate

ProPolymers Inc.

## Message:

Duron PBT 30GF is a general purpose 30% glass reinforced PBT that offers a superior combination of mechanical, electrical, and thermal properties. It is lubricated which improves mold release and surface finish. Duron PBT provides outstanding processability and good chemical resistance.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Lubricant		
Features	General Purpose		
	Good Chemical Resistance		
	Good Mold Release		
	Good Processability		
	Good Surface Finish		
	Lubricated		
Uses	General Purpose		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.53	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage			ASTM D955
Flow : 1.52 mm	0.30 to 0.50	%	
Flow : 3.18 mm	0.50 to 0.80	%	
Across Flow : 1.52 mm	0.40 to 0.60	%	
Across Flow : 3.18 mm	0.60 to 0.90	%	
Water Absorption (24 hr)	0.070	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	119	MPa	ASTM D638
Tensile Elongation (Break)	2.8	%	ASTM D638
Flexural Modulus	7580	MPa	ASTM D790
Flexural Strength	190	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	90	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	222	°C	
1.8 MPa, Unannealed	205	°C	

Melting Temperature	225	°C	
CLTE - Flow	2.0E-5	cm/cm/°C	ASTM D696

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

