

Sindustris PC GP5057F

Polycarbonate + ABS
Sincerity Australia Pty Ltd.

Message:

Sindustris PC GP5057F is a Polycarbonate + ABS (PC+ABS) material filled with 5.0% glass fiber. It is available in Asia Pacific for injection molding.
Important attributes of Sindustris PC GP5057F are:
Flame Rated
Flame Retardant
Typical applications include:
Electrical/Electronic Applications
Housings

General Information			
Filler / Reinforcement	Glass Fiber,5.0% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
	General Purpose		
Uses	Electrical/Electronic Applications		
	Housings		
UL File Number	E306922		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	2.5	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.35 to 0.55	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	70.1	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	6.0	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	3330	MPa	ASTM D790
Flexural Strength ⁴ (3.20 mm)	113	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	54	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	110	°C	ASTM D648
RTI Elec	60.0	°C	UL 746
RTI Imp	60.0	°C	UL 746
RTI Str	60.0	°C	UL 746
Flammability	Nominal Value	Test Method	
Flame Rating			UL 94

2.50 mm	V-0	
3.00 mm	V-0	
Injection	Nominal Value	Unit
Drying Temperature	75.0 to 85.0	°C
Drying Time	3.0 to 5.0	hr
Suggested Max Moisture	0.020	%
Rear Temperature	220 to 240	°C
Middle Temperature	235 to 255	°C
Front Temperature	250 to 265	°C
Nozzle Temperature	250 to 265	°C
Processing (Melt) Temp	235 to 265	°C
Mold Temperature	50.0 to 80.0	°C
Back Pressure	0.200 to 0.600	MPa
Screw Speed	40 to 70	rpm
NOTE		
1.	50 mm/min	
2.	50 mm/min	
3.	10 mm/min	
4.	10 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

