# megol® DP2433/50PBT

## Styrene Ethylene Butylene Styrene Block Copolymer API SpA

### Message:

megol® DP2433/50PBT is a Styrene Ethylene Butylene Styrene Block Copolymer (SEBS) product. It can be processed by injection molding and is available in Europe.

Characteristics include:

Chemical Resistant

Eco-Friendly/Green

Fast Molding Cycle

**Good Processability** 

Good UV Resistance

General Information				
Features	Acid Resistant			
	Base Resistant			
	Detergent Resistant			
	Fast Molding Cycle			
	Good Chemical Resistance			
	Good Processability			
	Good UV Resistance			
	Good Weather Resistance			
	High Heat Resistance			
	Low Compression Set			
	Low Temperature Resistant			
	Ozone Resistant			
	Recyclable Material			
Processing Method	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	0.960	g/cm³	ASTM D792	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A, 15 sec)	50		ASTM D2240	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength			ASTM D638	
	4.30	MPa		
100% Strain	1.80	MPa		
300% Strain	3.00	MPa		
Tensile Elongation (Break)	600	%	ASTM D638	
Elastomers	Nominal Value	Unit	Test Method	
Tear Strength <sup>1</sup>	24.0	kN/m	ASTM D624	
Compression Set			ASTM D395	

NOTE			
100°C, 24 hr	64	%	
70°C, 24 hr	47	%	
23°C, 72 hr	19	%	

1. Without Notch

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

