

# OTECH TPE OTE7532 - Cable Jacket

Thermoplastic Elastomer

OTECH Corporation

Message:

TRAY CABLE JACKET COMPOUNDS

Applications

TPE WIND POWER JACKET

General Information		
Uses	Jacketing	
	Wire and cable applications	
Physical	Nominal Value	Unit
Specific Gravity	1.32	g/cm <sup>3</sup>
Hardness	Nominal Value	Unit
Durometer Hardness (10 sec)	75	
Mechanical	Nominal Value	Unit
Tensile Strength	13.8	MPa
Tensile Elongation (Break)	350	%
Thermal	Nominal Value	
Cold shock (-25°C)	Pass	
Limited Oxygen Index	30	%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

