

SWANCOR Epoxy 901-35

Epoxy; Epoxide

SWANCOR IND. CO., LTD.

Message:

Low styrene content version of SWANCOR 901, with the same molecular weight providing excellent mechanical properties and chemical resistance as SWANCOR 901.

Cost saving alternative

| General Information | | | |
|--|------------------------------|------|-------------|
| Filler / Reinforcement | Styrene,35% Filler by Weight | | |
| Features | Acid Resistant | | |
| | Alkali Resistant | | |
| | Good Chemical Resistance | | |
| | Salt Water/Spray Resistant | | |
| Forms | Liquid | | |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (0.45 MPa, Unannealed) | 101 | °C | ASTM D648 |
| Thermoset | Nominal Value | Unit | Test Method |
| Shelf Life (25°C) | 39 | wk | |
| Thermoset Mix Viscosity (25°C) | 2500 | cP | ASTM D2393 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT