

TechnoDur PBT4 GK 20 Natural (9952)

Polybutylene Terephthalate

TechnoCompound GmbH

Message:

TechnoDur: Braves extremely low Temperatures

Our new TechnoDur PBT compound is a thermoplastic which combines great hardness, stiffness and strength. TechnoDur is easily processed due to its perfect flow behaviour. The favourable sliding and wear characteristics as well as extremely high tenacity in temperatures below freezing are further advantages.

Typical Applications

TechnoDur compounds may be applied in the following areas:

Electrical engineering: Lamp holders, micro switches, spools, brush-holder bridges, switches, cam divices, telephone housings...

Automobile construction: Junction boxes, petrol filters, fuel tank caps, heating, folds, headlights, car body panels, spark plug connectors...

Household appliances: Hair care appliances, components for toasters, fondue makers, coffeemakers...

Other: pump components, gears guide applications: slide bearings and components...

General Information			
Filler / Reinforcement	Glass beads, 20% filler by weight		
Features	Rigidity, high		
	High strength		
	Workability, good		
	Good liquidity		
	Low temperature resistance		
	Good wear resistance		
	High hardness		
Uses	Pump parts		
	Electrical/Electronic Applications		
	Electrical housing		
	Electrical appliances		
	Home appliance components		
	Switch		
	Application in Automobile Field		
Appearance	Bearing		
	Natural color		
Physical	Nominal Value	Unit	Test Method
Density	1.45	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	22.0	cm ³ /10min	ISO 1133
Molding Shrinkage ¹			ISO 2577
Transverse flow	1.6	%	ISO 2577
Flow	1.6	%	ISO 2577
Water Absorption			ISO 62

23°C, 24 hr	0.20	%	ISO 62
Saturated, 23°C	0.40	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness ²	165	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3800	MPa	ISO 527-2/1
Tensile Stress (Break)	50.0	MPa	ISO 527-2/5
Tensile Strain (Break)	5.0	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	3.0	kJ/m ²	ISO 179/1eA
23°C	3.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	30	kJ/m ²	ISO 179/1eU
23°C	30	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	175	°C	ISO 75-2/B
1.8 MPa, not annealed	70.0	°C	ISO 75-2/A
Vicat Softening Temperature	190	°C	ISO 306/B50
Melting Temperature ³	220 - 225	°C	ISO 11357-3
CLTE - Flow (23 to 80°C)	9.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+14	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Relative Permittivity			IEC 60250
100 Hz	4.40		IEC 60250
1 MHz	4.20		IEC 60250
Comparative Tracking Index (Solution A)	225	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.8 mm)	HB		Internal method
NOTE			
1.	260°C / WZ 80°C, 600 bar		
2.	358 N		
3.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

