Epoxies, Ect. 10-3783

Epoxy; Epoxide

Epoxies, Etc.

Message:

These one component heat cure epoxy adhesives are fast setting materials formulated in three different viscosities. They are known for their low temperature cure, heat and excellent chemical resistance.

Bondability

Medium viscosity

General Information

Features

These unique adhesives exhibit outstanding bond strengths to a variety of substrates including metals, ceramics, wood, magnets, plastics, glass, etc... They are currently used in a variety of electronic bonding and potting applications, filer end cap assemblies, magnetic bonding applications and anywhere a tough indestructible bond is required.

	Fast Cure		
	Good Adhesion Good Chemical Resistance		
	Medium Heat Resistance		
	Medium Viscosity		
Uses	Adhesives		
	Bonding		
	Caps		
Appearance	Grey		
Processing Method	Encapsulating		
	Potting		
Additional Information	Nominal Value	Unit	
Operating Temperature	-50.0 to 180	°C	
Uncured Properties	Nominal Value	Unit	
Color	Grey		
Solids Content	100	%	
Density (25°C)	1.49	g/cm³	
Viscosity (25°C)	60	Pa·s	
Curing Time			
175°C	0.030	hr	
160°C	0.083	hr	
121°C	0.25	hr	
121°C 100°C	0.25 2.0	hr hr	
100°C			

Cured Properties	Nominal Value	Unit	
Shore Hardness			
Shore D, 121°C	70		
Shore D, 25°C	80		
Tensile Strength	27.6	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

