

Riblene® FL 39 D

Low Density Polyethylene

Versalis S.p.A.

Message:

Riblene FL 39 D is a low density polyethylene (LDPE) ideal for blown film extrusion. Riblene FL 39 D is characterised by a good balance between processability, mechanical and optical properties

Films manufactured by Riblene FL 39 D are easily heat shrinkable.

Main Application

Riblene FL 39 D is recommended for general blown film applications, for the production of low gauge film and shrink film, for lamination and for blend.

General Information			
Features	Food Contact Acceptable Good Heat Shrinkability Good Processability Low Density Opticals		
Uses	Blending Film Laminates Shrink Wrap		
Agency Ratings	EU Food Contact, Unspecified Rating		
Forms	Pellets		
Processing Method	Blown Film Film Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.924	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.2	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction (vs. Itself - Dynamic, Blown Film)	> 0.50		ISO 8295
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	40	µm	
Film Thickness - Recommended / Available	25 to 80 µm		
Tensile Modulus			ISO 527-3
1% Secant, MD : 40 µm, Blown Film	180	MPa	
1% Secant, TD : 40 µm, Blown Film	190	MPa	
Tensile Stress			ISO 527-3
MD : Yield, 40 µm, Blown Film	11.0	MPa	

TD : Yield, 40 µm, Blown Film	11.0	MPa	
MD : Break, 40 µm, Blown Film	25.0	MPa	
TD : Break, 40 µm, Blown Film	22.0	MPa	
Tensile Elongation			ISO 527-3
MD : Break, 40 µm, Blown Film	300	%	
TD : Break, 40 µm, Blown Film	650	%	
Dart Drop Impact ¹ (40 µm, Blown Film)	130	g	ISO 7765-1
Elmendorf Tear Strength ²			ISO 6383-2
MD : 40.0 µm	80.0	kN/m	
TD : 40.0 µm	55.0	kN/m	
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -75.0	°C	ASTM D746
Vicat Softening Temperature	93.0	°C	ISO 306/A
Melting Temperature	114	°C	Internal Method
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 40.0 µm, Blown Film)	74		ASTM D2457
Haze (40.0 µm, Blown Film)	5.0	%	ISO 14782
Extrusion	Nominal Value	Unit	
Melt Temperature	160 to 190	°C	
NOTE			
1.	F50		
2.	Blown Film		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

