

Clariant Nylon 6 R60G33-L

Polyamide 6

Clariant Corporation

Message:

Clariant Nylon 6 R60G33-L is a Polyamide 6 (Nylon 6) material filled with 33% glass fiber. It is available in North America. Primary attribute of Clariant Nylon 6 R60G33-L: Lubricated.

General Information			
Filler / Reinforcement	Glass Fiber,33% Filler by Weight		
Additive	Lubricant		
Features	Lubricated		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.36	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.40	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	117	MPa	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	6890	MPa	ASTM D790
Flexural Strength	179	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	69	J/m	ASTM D256
Tensile Impact Strength	11.3	kJ/m ²	ASTM D1822
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	204	°C	
1.8 MPa, Unannealed	191	°C	
Melting Temperature	216 to 221	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT