

RAMSTER RF350M3

Polybutylene Terephthalate

Polyram Ram-On Industries

Message:

INDUSTRIAL GRADE 15% MINERAL FILLED P.B.T FOR INJECTION MOULDING APPLICATIONS.

General Information			
Filler / Reinforcement	Mineral filler, 15% filler by weight		
Uses	Industrial application		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	20	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			
Flow	1.8	%	ASTM D955
--	1.8	%	ISO 2577
Water Absorption			
Saturation	0.50	%	ASTM D570
Saturated, 23°C	0.50	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2900	MPa	ASTM D638, ISO 527-2
Tensile Strength (Yield)	55.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation			
Fracture	3.5	%	ASTM D638
Fracture	15	%	ISO 527-2
Flexural Modulus	3000	MPa	ASTM D790, ISO 178
Flexural Strength	95.0	MPa	ASTM D790, ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	50	J/m	ASTM D256
23°C	5.5	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	225	°C	ISO 11357-3, ASTM D3418
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	3.6	ohms	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.00 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	

Drying Time	3.0 - 4.0	hr
Suggested Max Moisture	0.050	%
Rear Temperature	235 - 255	°C
Middle Temperature	240 - 260	°C
Front Temperature	245 - 270	°C
Processing (Melt) Temp	240 - 270	°C
Mold Temperature	70.0 - 90.0	°C
Injection Pressure	70.0 - 105	MPa
Holding Pressure	30.0 - 105	MPa
Back Pressure	0.350 - 0.700	MPa
Screw Speed	60 - 90	rpm

Injection instructions

Fill Speed: 25 to 50 mm/sec

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

