

ELASTOSIL® R plus 4070/60

Silicone

Wacker Chemie AG

Message:

Silicone Rubber, HTV

Technical Textiles, Technical Textiles

Coating of Fabrics and Textiles, Technical Textiles

Molded Parts, Technical, Plastics and Rubber Processing

General Information			
Uses	Fabric Coatings		
	Industrial Applications		
	Overmolding		
Processing Method	Coating		
	Compression Molding		
	Press Molding		
Uncured Properties	Nominal Value	Unit	Test Method
Color	Translucent		
Density	1.17	g/cm ³	ISO 1183
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	62		DIN 53505
Tensile Strength	10.0	MPa	DIN 53504
Tensile Elongation at Break	650	%	DIN 53504
Compression Set	75	%	DIN ISO 815-B
Tear Strength	43.0	kN/m	ASTM D624B
Rebound Resilience	40	%	DIN 53512

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 1342475533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT