

GPPC ABS D-120S

Acrylonitrile Butadiene Styrene

GPPC Chemical Co., Ltd.

Message:

GPPC ABS D-120S is an Acrylonitrile Butadiene Styrene (ABS) material. It is available in Asia Pacific or North America for extrusion or injection molding. Important attributes of GPPC ABS D-120S are:
REACH Compliant
RoHS Compliant

General Information			
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.03	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)			
200°C/5.0 kg	0.60	g/10 min	ASTM D1238
220°C/10.0 kg	6.0	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	104		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (3.18 mm)	42.9	MPa	ASTM D638
Flexural Modulus ² (3.18 mm)	2170	MPa	ASTM D790
Flexural Strength ³ (3.18 mm)	74.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
3.18 mm	490	J/m	
6.35 mm	410	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 12.7 mm)	90.0	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 90.0	°C	
Processing (Melt) Temp	170 to 240	°C	
Mold Temperature	40.0 to 80.0	°C	
NOTE			
1.	50 mm/min		
2.	15 mm/min		
3.	15 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

