# KRATON® D2109 DS-W

### Styrene Butadiene Styrene Block Copolymer

#### Kraton Polymers LLC

#### Message:

Kraton D2109 DS-W is an easy processing, general purpose 45 Shore A hardness material designed for a wide variety of applications. It is supplied from North America in the physical form identified below. Kraton D2109 DS-W - supplied as a dense, white pellet

General Information **General Purpose** Features Good Processability **Recyclable Material** Uses **General Purpose** Appearance White Forms Pellets Processing Method Extrusion Injection Molding Thermoforming Physical Nominal Value Unit Test Method 0.915 to 0.945 Specific Gravity g/cm<sup>3</sup> Internal Method g/10 min Melt Mass-Flow Rate (MFR) (200°C/5.0 kg) 14 to 24 ASTM D1238 % ASTM D955 Molding Shrinkage - Flow 2.5 to 2.7 Hardness Nominal Value Unit Test Method Durometer Hardness (Shore A, Compression Molded) 40 to 50 Internal Method Elastomers Nominal Value Unit Test Method Tensile Stress<sup>1</sup> ASTM D412 Across Flow : 100% Strain 1.03 MPa Flow : 100% Strain 1.38 MPa Across Flow : 300% Strain 1.72 MPa Flow : 300% Strain 2.07 MPa Tensile Strength<sup>2</sup> ASTM D412 Across Flow : Yield 4.83 MPa Flow : Yield 3.45 MPa Tensile Elongation <sup>3</sup> ASTM D412 Across Flow : Break 800 % Flow : Break 550 % Tear Strength<sup>4</sup> ASTM D624 Across Flow 26.3 kN/m

| Flow               | 21.9           | kN/m |  |
|--------------------|----------------|------|--|
| Injection          | Nominal Value  | Unit |  |
| Rear Temperature   | 171 to 182     | °C   |  |
| Front Temperature  | 188 to 199     | °C   |  |
| Nozzle Temperature | 177 to 193     | °C   |  |
| Mold Temperature   | 10.0 to 37.8   | °C   |  |
| Injection Pressure | 3.45 to 4.83   | МРа  |  |
| Injection Rate     | Moderate-Fast  |      |  |
| Back Pressure      | 0.276 to 0.414 | МРа  |  |
| NOTE               |                |      |  |
| 1.                 | Die C          |      |  |
| 2.                 | Die C          |      |  |
| 3.                 | Die C          |      |  |
| 4.                 | Die C          |      |  |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

