

ELASTOSIL® R 416/70

Silicone

Wacker Chemie AG

Message:

Silicone Rubber, HTV

Hoses, Automotive, Automotive & Transportation

Extrudates, Automotive, Plastics and Rubber Processing

Extrudates, Automotive, Automotive & Transportation

Extrudates, Technical, Plastics and Rubber Processing

General Information	
Uses	Automotive Applications
	Automotive Under the Hood
	Compounding
	Hose
	Profiles
Processing Method	Calendering
	Extrusion
	Profile Extrusion

Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	70		DIN 53505
Tensile Strength	10.0	MPa	DIN 53504
Tensile Elongation at Break	570	%	DIN 53504
Compression Set	20	%	DIN ISO 815-B
Tear Strength	30.0	kN/m	ASTM D624B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT