Yuyao PA 03ML20

Polyamide 66/6 Copolymer

Yuyao Tenglong Plastics Co., Ltd.

Message:

Yuyao PA 03ML20 is a Polyamide 66/6 Copolymer (Nylon 66/6) product. It can be processed by injection molding and is available in Asia Pacific. Applications of Yuyao PA 03ML20 include electrical/electronic applications, appliances, automotive and tools.

Characteristics include

Flame Rated

Flame Retardant

Good Processability

General Information

Halogen Free

Heat Resistant

General Information					
Additive	Flame Retardant				
Features	Flame Retardant				
	Good Electrical Properties				
	Good Processability				
	Halogen Free				
	High Heat Resistance				
	High Strength				
Uses	Appliance Components				
	Automotive Under the Hood				
	Communication Applications				
	Computer Components				
	Connectors				
	Electrical Parts				
	Power/Other Tools				
Processing Method	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.28	g/cm³	ASTM D792		
Molding Shrinkage - Flow	0.50 to 0.80	%	ASTM D955		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength	100	MPa	ASTM D638		
Tensile Elongation (Break)	6.0	%	ASTM D638		
Flexural Modulus	4600	MPa	ASTM D790		
Flexural Strength	130	MPa	ASTM D790		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact (Area)	9.00	kJ/m²	ASTM D256		
Thermal	Nominal Value	Unit	Test Method		

Deflection Temperature Under Load (1.8			
MPa, Unannealed)	150	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	V-0		
3.20 mm	V-0		
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 95.0	°C	
Drying Time	5.0 to 8.0	hr	
Processing (Melt) Temp	220 to 270	°C	
Mold Temperature	40.0 to 80.0	°C	
Injection Pressure	80.0 to 100	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

