Novamid® 1007J

Polyamide 6

DSM Engineering Plastics

Message:

Novamid® 1007J is a Polyamide 6 (Nylon 6) material. It is available in Asia Pacific for injection molding. Primary attribute of Novamid® 1007J: Low Viscosity.

General Information			
Features	Low Viscosity		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm³	ISO 1183
Water Absorption (Equilibrium, 23°	C, 50%		
RH)	2.8	%	ISO 62
Viscosity Number	99.0	cm³/g	ISO 307
Thermal	Nominal Value	Unit	Test Method
Melting Temperature ¹	220	°C	ISO 11357-3
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0 to 8.0	hr	
Rear Temperature	230 to 235	°C	
Middle Temperature	235 to 250	°C	
Front Temperature	240 to 260	°C	
Nozzle Temperature	240 to 270	°C	
Processing (Melt) Temp	240 to 275	°C	
Mold Temperature	50.0 to 80.0	°C	
Injection Rate	Moderate-Fast		
Back Pressure	3.00 to 10.0	MPa	
Screw Compression Ratio	2.5:1.0		
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

