

LNP™ THERMOCOMP™ SF008 compound

Polyamide 12

SABIC Innovative Plastics

Message:

LNP THERMOCOMP SF008 is a compound based on Nylon 12 resin containing Glass Fiber.

Also known as: LNP* THERMOCOMP* Compound SF-1008

Product reorder name: SF008

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.37	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow: 24 hours	0.20	%	ASTM D955
Transverse flow: 24 hours	0.70	%	ASTM D955
Vertical flow direction: 24 hours	0.73	%	ISO 294-4
Flow direction: 24 hours	0.18	%	ISO 294-4
Water Absorption (24 hr, 50% RH)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	8270	MPa	ASTM D638
--	8760	MPa	ISO 527-2/1
Tensile Strength			
Fracture	136	MPa	ASTM D638
Fracture	152	MPa	ISO 527-2
Tensile Elongation			
Fracture	11	%	ASTM D638
Fracture	9.0	%	ISO 527-2
Flexural Modulus			
--	7580	MPa	ASTM D790
--	9000	MPa	ISO 178
Flexural Strength			
--	96.5	MPa	ASTM D790
--	213	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	260	J/m	ASTM D256
23°C ²	18	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	1400	J/m	ASTM D4812

23°C ³	76	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	177	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	170	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ⁴	166	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.12 - 0.20	%	
Rear Temperature	216 - 227	°C	
Middle Temperature	221 - 232	°C	
Front Temperature	227 - 238	°C	
Processing (Melt) Temp	227 - 238	°C	
Mold Temperature	71.1 - 82.2	°C	
Back Pressure	0.172 - 0.344	MPa	
Screw Speed	30 - 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

