TIPOLEN® FB 243-55

Low Density Polyethylene

MOL Petrochemicals Co. Ltd.

Message:

TIPOLEN FB 243-55 is a film grade of low density polyethylene with good mechanical properties and excellent processability. The grade contains slip and antiblocking agents.

Applications

TIPOLEN FB 243-55 is intended for shopping bags, packaging films, household films. Recommended film thickness is 0.04-0.10 mm. TIPOLEN FB 243-55 is suitable for food contact. The product complies with Food Contact Regulations.

General Information				
Additive	Antiblock (800 ppm)			
	Slip (400 ppm)			
Features	Antiblocking			
	Food Contact Acceptable			
	Good Processability			
	Recyclable Material			
	Slip			
Uses	Bags			
	Film			
	Household Goods			
Forms	Pellets			
Processing Method	Film Extrusion			
Physical	Nominal Value	Unit	Test Method	
Density	0.921	g/cm³	ISO 1183	
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.75	g/10 min	ISO 1133	
Hardness	Nominal Value	Unit	Test Method	
Shore Hardness (Shore D)	48	01mt	ISO 868	
Films	Nominal Value	Unit	Test Method	
Film Thickness - Tested	40	μm		
Film Thickness - Recommended / Available	0.04 to 0.10 mm	F		
Tensile Strength			ISO 527-3	
MD : 40 µm, Blown Film	25.0	MPa	-	
TD : 40 µm, Blown Film	20.0	MPa		
Tensile Elongation			ISO 527-3	
MD : Break, 40 µm, Blown Film	230	%		
TD : Break, 40 µm, Blown Film	550	%		
Dart Drop Impact (40 µm, Blown Film)	130	g	ISO 7765-1	

Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	96.0	°C	ISO 306/A120
Optical	Nominal Value	Unit	Test Method
Haze (40.0 µm, Blown Film)	11	%	ISO 14782
Extrusion	Nominal Value	Unit	
Melt Temperature	170 to 190	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

