

Durethan® BG 30 X FN01 000000

Polyamide 6

LANXESS GmbH

Message:

PA 6, 30 % glass fibers/glass spheres, injection molding, halogen free flame retardant, improved flowability, improved surface finish

General Information				
UL YellowCard		E245249-101565549	E245249-101786024	
Filler / Reinforcement		Glass Bead\Glass Fiber,30% Filler by Weight		
Additive		Flame Retardant		
Features		Flame Retardant		
		Good Flow		
		Good Surface Finish		
		Halogen Free		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.39	--	g/cm ³	ISO 1183
Apparent Density	0.70	--	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (260°C/2.16 kg)	27.0	--	cm ³ /10min	ISO 1133
Molding Shrinkage				ISO 2577
Across Flow : 260°C, 2.00 mm ¹	0.70	--	%	
Across Flow : 120°C, 4 hr, 2.00 mm ²	0.10	--	%	
Flow : 260°C, 2.00 mm ³	0.40	--	%	
Flow : 120°C, 4 hr, 2.00 mm ⁴	0.10	--	%	
Water Absorption				ISO 62
Saturation, 23°C	5.3	--	%	
Equilibrium, 23°C, 50% RH	1.6	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	7200	3500	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	100	50.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.0	7.0	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	7000	3700	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% Strain,23°C	--	80.0	MPa	
23°C ⁶	145	90.0	MPa	

Flexural Strain at Flexural Strength ⁷ (23°C)	3.1	5.6	%	ISO 178/A
ISO Shortname	PA 6, GFHR, 12-070, (GB+GF)30;-ISO 1043-PA GF FR (30+40)			ISO 1874
Residual Moisture Content	0.030 to 0.070			Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	< 10	< 10	kJ/m ²	
23°C	< 10	10	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	35	35	kJ/m ²	
23°C	40	45	kJ/m ²	
Notched Izod Impact Strength				ISO 180/1A
-30°C	< 10	< 10	kJ/m ²	
23°C	< 10	10	kJ/m ²	
Unnotched Izod Impact Strength (23°C)	35	38	kJ/m ²	ISO 180/1U
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	214	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	190	--	°C	ISO 75-2/A
Vicat Softening Temperature	203	--	°C	ISO 306/B120
Ball Pressure Test (206°C)	Pass	--		IEC 60695-10-2
Melting Temperature ⁸	222	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C	3.0E-5	--	cm/cm/°C	
Transverse : 23 to 55°C	8.0E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Electric Strength (23°C, 1.00 mm)	32	--	kV/mm	IEC 60243-1
Comparative Tracking Index (CTI)	PLC 0	--		UL 746
Comparative Tracking Index (Solution A)	575	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.750 mm	V-0	--		
1.50 mm	V-0	--		
3.00 mm	V-0	--		
2.00 mm	5VA	--		
Glow Wire Flammability Index				IEC 60695-2-12

0.750 mm	960	--	°C	
1.50 mm	960	--	°C	
3.00 mm	960	--	°C	
Oxygen Index ⁹	35	--	%	ISO 4589-2
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 to 6.0		hr	
Processing (Melt) Temp	250 to 270		°C	
Mold Temperature	80.0 to 100		°C	

NOTE

- | | |
|----|-----------------------------|
| 1. | 60x60x2mm, 80°C MT, 600 bar |
| 2. | 60x60x2mm |
| 3. | 60x60x2mm, 80°C MT, 600 bar |
| 4. | 60x60x2mm |
| 5. | 2.0 mm/min |
| 6. | 2.0 mm/min |
| 7. | 2 mm/min |
| 8. | 10°C/min |
| 9. | Procedure A |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT