

LNP™ THERMOCOMP™ PB006EQ compound

Polyamide 6

SABIC Innovative Plastics Europe

Message:

LNP *THERMOCOMP* PB006EQ is a compound based on PA 6 containing Glass Bead. Added features include Reduced Moisture.

General Information			
Filler / Reinforcement	Glass Bead		
Features	Low Moisture Absorption		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.26	g/cm ³	ISO 1183
Molding Shrinkage - Flow	1.8	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	42.0	MPa	ISO 527-2/5
Tensile Strain (Break)	10	%	ISO 527-2/5
Flexural Modulus ¹	2400	MPa	ISO 178
Flexural Stress	56.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ² (23°C)	4.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ³ (23°C)	40	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁴ (1.8 MPa, Unannealed, 64.0 mm Span)	61.0	°C	ISO 75-2/Af
CLTE			ISO 11359-2
Flow : 23 to 60°C	1.1E-4	cm/cm/°C	
Transverse : 23 to 60°C	1.2E-4	cm/cm/°C	
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15 to 0.25	%	
Rear Temperature	249 to 260	°C	
Middle Temperature	254 to 266	°C	
Front Temperature	266 to 277	°C	
Processing (Melt) Temp	254 to 277	°C	
Mold Temperature	82.2 to 93.3	°C	
Back Pressure	0.344 to 0.689	MPa	
Screw Speed	30 to 60	rpm	
NOTE			

1.	2.0 mm/min
2.	80*10*4
3.	80*10*4
4.	80*10*4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

