

APICAL 200NP

PI Film
Kaneka North America LLC

Message:
APICAL 200NP is a PI Film material. It is available in Latin America or North America.

General Information			
Forms	Film		
Physical	Nominal Value	Unit	Test Method
Water Absorption (23°C, 24 hr)	< 3.8	%	IPC TM-650 2.6.2
Films	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D882A
MD : Break	> 228	MPa	
TD : Break	> 228	MPa	
Tensile Elongation			ASTM D882A
MD : Break	> 50	%	
TD : Break	> 50	%	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (200°C)	> 1.0E+12	ohms·cm	ASTM D257
Dielectric Strength ¹ (in Air)	> 200	kV/mm	ASTM D149
Dielectric Constant (1 kHz)	< 3.90		ASTM D150
Dissipation Factor (1 kHz)	< 3.5E-3		ASTM D150
NOTE			
1.	500 V/sec		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT