

VITAMIDE® AR37BK8524

Polyamide 66

Jackdaw Polymers

Message:

VITAMIDE® AR37BK8524 is a Polyamide 66 (Nylon 66) product filled with 35% glass fiber. It is available in Europe, Latin America, or North America. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	Glass Fiber,35% Filler by Weight		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm ³	ASTM D792, ISO 1183
Water Absorption			
24 hr	0.70	%	ASTM D570
23°C, 24 hr	0.70	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			
Break	195	MPa	ISO 527-2
--	195	MPa	ASTM D638
Tensile Elongation (Break)	3.5	%	ASTM D638, ISO 527-2
Flexural Modulus	9000	MPa	ASTM D790, ISO 178
Flexural Strength	250	MPa	ASTM D790, ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	11	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	240	°C	ASTM D648, ISO 75-2/B
1.8 MPa, Unannealed	230	°C	ASTM D648, ISO 75-2/A
Melting Temperature	258	°C	ISO 1218, ASTM D2117
CLTE - Flow	2.5E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	ASTM D257, IEC 60093
Dielectric Strength	24	kV/mm	ASTM D149, IEC 60243-1
Comparative Tracking Index			
Solution A	450	V	IEC 60112
--	450	V	ASTM D3638
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Oxygen Index	23	%	ASTM D2863, ISO 4589-2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

