

Cevian®-V T550, T550SF

Acrylonitrile Butadiene Styrene

Daicel Polymer Ltd.

Message:

Cevian®-V T550, T550SF is an Acrylonitrile Butadiene Styrene (ABS) material. It is available in Asia Pacific. Primary attribute of Cevian®-V T550, T550SF: Flame Rated.

General Information			
UL YellowCard	E47773-616233		
Physical	Nominal Value	Unit	Test Method
Density	1.11	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	28	g/10 min	ISO 1133
Molding Shrinkage - Flow	0.40 to 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	48.0	MPa	ISO 527-2
Flexural Modulus	2300	MPa	ISO 178
Flexural Stress	74.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	9.0	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	73.0	°C	ISO 75-2/A
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Optical	Nominal Value	Unit	Test Method
Transmittance (3000 μm)	90.0	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 85.0	°C	
Drying Time	3.0 to 5.0	hr	
Rear Temperature	170 to 190	°C	
Middle Temperature	190 to 210	°C	
Front Temperature	210 to 230	°C	
Nozzle Temperature	210 to 230	°C	
Mold Temperature	40.0 to 60.0	°C	
Back Pressure	10.0 to 20.0	MPa	
Screw Speed	70 to 90	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

