

# Generic Phenolic - Graphite Powder

Phenolic

Generic

## Message:

This data represents typical values that have been calculated from all products classified as: Generic Phenolic - Graphite Powder  
This information is provided for comparative purposes only.

General Information		
Filler / Reinforcement	Graphite powder	
Injection	Nominal Value	Unit
Mold Temperature	174 - 177	°C
Back Pressure	0.300 - 10.0	MPa
Injection instructions		

This data represents typical values that have been calculated from all products classified as: Generic Phenolic - Graphite Powder  
This information is provided for comparative purposes only.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

