

SABIC® LDPE HP0722N

Low Density Polyethylene

SABIC Americas, Inc.

Message:

Product Description

HP0722N is Low Density Polyethylene grade suitable for producing medium duty films and contains no slip and antiblock additives. It gives good toughness and optical properties in the film.

Typical Applications

HP0722N can be used for medium duty bags, shrink films, shopping bags, lamination films and frozen food packaging.

General Information			
Features	Low density		
	Optical		
	Good toughness		
	Compliance of Food Exposure		
Uses	Films		
	Laminate		
	Bags		
	Food packaging		
	Shrinkable film		
Forms	Particle		
Processing Method	Blow film		
Physical	Nominal Value	Unit	Test Method
Density	0.922	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/21.6 kg)	0.75	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	50	µm	
secant modulus			ASTM D882
1% secant, MD: 50 µm, blown film	180	MPa	ASTM D882
1% secant, TD: 50 µm, blown film	200	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Yield, 50 µm, blown film	10.0	MPa	ASTM D882
TD: Yield, 50 µm, blown film	9.00	MPa	ASTM D882
MD: Broken, 50 µm, blown film	27.0	MPa	ASTM D882
TD: Broken, 50 µm, blown film	23.0	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Broken, 50 µm, blown film	400	%	ASTM D882
TD: Broken, 50 µm, blown film	650	%	ASTM D882
Dart Drop Impact (50 µm, Blown Film)	200	g	ASTM D1709

Elmendorf Tear Strength			ASTM D1922
MD: 50 µm, blown film	350	g	ASTM D1922
TD: 50 µm, blown film	280	g	ASTM D1922
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	95.0	°C	ASTM D1525
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 50.0 µm, Blown Film)	60		ASTM D2457
Haze (50.0 µm, Blown Film)	9.0	%	ASTM D1003
Additional Information	Nominal Value		
Blow-up Ratio	2.50 - 4.00		
Properties have been measured by producing 50 µ film with 2.5 BUR using 100% HP0722N.			
Extrusion	Nominal Value	Unit	
Melt Temperature	170 - 185	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

