Dryflex® 500550S

Styrene Ethylene Butylene Styrene Block Copolymer

ELASTO

Message:

The 500S series is very favourable when transparency and good scratch resistance are required, as well as when there are high surface finish requirements. Unfilled grades have excellent flow and mechanical properties, such as elongation, compression set, tensile and tear strength. The low density entails lower weight compared to the 600S and 660S series. Unfilled compounds are available in hardness from 0 Shore A to 55 Shore D in translucent and black colours but they can easily be coloured in any shade.

| General Information | | | |
|---------------------------------------|--------------------------|----------|-------------|
| Features | Bondability | | |
| | Food Contact Acceptable | | |
| | Good Chemical Resistance | | |
| | Good Weather Resistance | | |
| | Scratch Resistant | | |
| | | | |
| Appearance | Translucent | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 0.890 | g/cm³ | ASTM D792 |
| Melt Mass-Flow Rate (MFR) (190°C/2.16 | | | |
| kg) | 1.0 | g/10 min | ASTM D1238 |
| Molding Shrinkage | 0.80 to 2.0 | % | |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A) | 55 | | ASTM D2240 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | | | ASTM D638 |
| | 6.00 | MPa | |
| 100% Strain | 2.00 | MPa | |
| 300% Strain | 3.00 | MPa | |
| Tensile Elongation (Break) | > 600 | % | ASTM D638 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tear Strength | 24.0 | kN/m | ASTM D624 |
| Compression Set (23°C, 72 hr) | 20 | % | ASTM D395 |
| Thermal | Nominal Value | Unit | |
| Service Temperature | -50 to 125 | °C | |
| Injection | Nominal Value | Unit | |
| Processing (Melt) Temp | 180 to 210 | °C | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

